



15 Mercedes Drive
Montvale, NJ 07645 U.S.A.
Telephone: 201.791.4020
Fax: 201.791.1637
www.coininginc.com



ELECTRONIC COMPONENTS
AND PACKAGING

63 Silver - 27 Copper-10 Indium

Physical Properties of Bulk Solder

Solder Alloy Composition	Ag63Cu27In10 (weight per cent)
Solidus temperature	685°C (1265°F)
Liquidus temperature	730°C (1345°F)
Density	9.62 kg/l
Yield strength	345 MPa
Tensile strength	420 MPa
Thermal conductivity	85 W/(m.K)
Thermal Coefficient of Expansion	$19.6 \times 10^{-6} \text{ K}^{-1}$
Electrical Resistivity	9.0 $\mu\Omega$ cm

Typical impurity levels for electronic grade/ vacuum tube grade are less than:

Pb: 0.002 Zn: 0.001 P : 0.002 Mn: 0.001

Cd: 0.001 C : 0.005

Volatile elements each 0.001 % max.

Other elements each 0.001% max.

Total other elements 0.010% max.

AgCu-alloys are generally used to join, silver, copper and nickel base alloys in reducing or inert atmospheres or vacuum. They are also widely used to join metallized ceramics to metals in vacuum. This assumes reasonably-clean brazing surfaces or controlled atmosphere during the brazing cycle. If and when the components are slightly oxidized, a combination with higher temperatures and/or longer brazing temperatures is required.

Joint clearance is recommended at 0.002" - .005" (50-127 μ m).

During remelting joints on either copper- or silver-base alloys, the braze exhibits decreased fluidity and an increased remelt temperature, due to the solution of either silver or copper in the eutectic. Brazing time and temperature should be minimized to prevent excessive diffusion and erosion of the base metal.

AgCu-based filler materials have limited wetting ability on iron and/or nickel base alloys. The wetting it does have is derived primarily from its copper content. Both nickel and iron have practically no solubility in silver, while nickel is readily soluble in copper and the solubility of iron in copper is sufficient to provide wetting. The addition of indium to the AgCu-alloy enables good wetting to Ni and Ni-alloys (Kovar). It further lowers the solidus temperature enabling step- or cascade brazing of eutectic-brazed subassemblies.

The information contained herein is based on data considered accurate and is offered at no charge. No warranty is expressed or implied regarding the accuracy of this data. Liability is expressly disclaimed for any loss or injury arising out of the use of this information or the use of any materials designated.