




15 Mercedes Drive
Montvale, NJ 07645 U.S.A.
Telephone: 201.791.4020
Fax: 201.791.1637
www.coininginc.com



ELECTRONIC COMPONENTS
AND PACKAGING

Data Sheet: 60 Tin-40 Lead

Physical Properties of Bulk Solder

Solder Alloy Composition	Sn60-Pb40 (weight per cent)
Solidus	183°C
Liquidus	188°C
Density	8.52 Mg/m ³
Coefficient of Thermal Expansion	23.9 x 10 ⁻⁶ K ⁻¹
Young's Modulus	29.99 Nmm ⁻²
Hardness	16 HV
Thermal Conductivity	50 W m ⁻¹ K ⁻¹
Electrical Conductivity	11.5% IACS
Electrical Resistivity	14.99 μΩ cm

Mechanical Properties: Tensile Strength (Stress, Nmm⁻²)

		<u>20°C</u>	<u>100°C</u>
Test speed	50 mm min ⁻¹	66.6	31.2
	20	50.0	28.2
	5.0	46.5	19.6
	1.0	38.2	12.7
	0.2	32.0	7.4
	0.05	18.7	3.9

Typical impurity levels for electronic grade are less than:

Au: 0.05	Cu: 0.08	Ni: 0.01	Al: 0.005
Bi: 0.10	Fe: 0.02	Zn: 0.003	As: 0.03
Cd: 0.002	In: 0.10		

Soldering temperature for reflow should be minimal at or above 235°C for a minimal time of 20 seconds. This assumes either very clean, soldering surfaces and an inert or reducing atmosphere or the presence of a deoxidizing agent/flux during the soldering cycle. If and when the components are slightly oxidized, a combination with higher temperatures and/or longer soldering temperatures is required. For more oxidized surfaces, an appropriate flux must be used.

The information contained herein is based on data considered accurate and is offered at no charge. No warranty is expressed or implied regarding the accuracy of this data. Liability is expressly disclaimed for any loss or injury arising out of the use of this information or the use of any materials designated.